
Ocono
Ruhrkunststoff

GENESIS® MK II

Light weight flexible profile hose made of PE



Applications	blowing in insulation material, extraction systems, asbestos removal, swimming pool technology, construction machines
Structure	PE, translucent, plastic spiral / PE
Temperature	-40°C up to 60°C
Properties	very good chemical resistance, crush-resistant, ultimate elongation, good tensile strength, floatable, free of halogen & softeners





made in Germany

Inner Diameter (mm)	Outer Diameter (mm)	Wall Thickness (mm)	Bending Radius (mm)	Max. Operating Pressure (bar)	Vacuum Max. (bar)	Total Weight per Piece (kg)	Length (m)	Article Number
38	50,00	0,70	60	1,30	0,60	3,04	10	43100038-1000-000-00
38	50,00	0,70	60	1,30	0,60	4,55	15	43100038-1500-000-00
51	63,00	0,70	80	1,00	0,50	4,09	10	43100051-1000-000-00
51	63,00	0,70	80	1,00	0,50	6,13	15	43100051-1500-000-00
63	75,00	0,70	100	0,80	0,40	4,85	10	43100063-1000-000-00
63	75,00	0,70	100	0,80	0,40	7,27	15	43100063-1500-000-00
76	88,00	0,70	120	0,50	0,30	5,79	10	43100076-1000-000-00
76	88,00	0,70	120	0,50	0,30	8,68	15	43100076-1500-000-00
90	102,00	0,70	140	0,40	0,20	10,20	15	43100090-1500-000-00
102	114,00	0,70	160	0,30	0,20	7,67	10	43100102-1000-000-00
102	114,00	0,70	160	0,30	0,20	11,51	15	43100102-1500-000-00

Ocono Ruhrkunststoff GmbH | Weseler Str. 35 | 45478 Mülheim an der Ruhr | Germany | T +49 208 99910 | rk@ocono.com

All technical data, measured at 23°C, are general orientation values and are subject to production-related tolerances. Max. operating pressures apply only for short periods. Technical changes and color deviations are subject to change. Other versions are available upon request.
Date: 24.11.2026